

**TECHNICAL DATA SHEET
ТЕХНИЧЕСКИЙ ПАСПОРТ****ПИГМЕНТ ЖЕЛЕЗООКИСНЫЙ (КОРИЧНЕВЫЙ BROWN 686, КИТАЙ)**

Показатель	Значения
Color Shade (ΔE) max	1.0
Tinting Strength %	95-105
Water-Soluble Content [%] max	0.5
Sieve Residue (0.045mm) [%] max	0.5
PH Value	4.0-7.0
Fe ₂ O ₃ & Fe ₃ O ₄ [%] min	90
Moisture (After Production) [%] max	1.0
Oil Absorption [g/100g]	15-35